

Mobilect 39

Electrical insulating oils

Product Description

Mobilect 39 is a high quality mineral uninhibited insulating oils with very good dielectric properties and oxidation stability intended for transformers, switchgears and other electrical equipment.

Mobilect 39 is uninhibited and meets the specifications IEC 60296-03 (U) and ASTM D1275B / CIGRE corrosion tests requirements.

Features and Benefits

- Mobilect 39 has a high resistance to thermal and chemical degradation in the presence of iron and copper, which reduces tendencies to produce sludges and oil-soluble oxidation products. When lower quality oils are used these may form deposits in the transformer and impede heat transfer by interfering with convection currents. In addition deposits may accelerate insulation defects and are often very difficult to remove without complete dismantling.
- Mobilect 39 is specifically treated during manufacture to remove moisture. Water will reduce the electrical insulating properties of the oil and promote oxidation. It is important to remember that a dry oil is hygroscopic and absorbs moisture from the air. It must therefore always be stored in dry conditions and well-closed containers. It is strongly recommend to dry the product before use or use it within short notice after purchasing to avoid long term storage.
- The dielectric strength of Mobilect 39 is a measure of the resistance of the oil to electric stress and is expressed in kV across a specified gap under test conditions. This is not a measure of the quality of the oil but of the absence of contaminants - especially moisture, fibres and polar chemicals.
- Mobilect 39 is free from wax even at low temperatures and thus circulates freely in outdoor applications. Its viscosity ensures readily heat transfer by mobile convection currents. Mobility is also essential to quick quenching of arcs in switchgear units.
- The low pour point of Mobilect 39 ensures a free flow in most conditions between the transformer and the conservator and maintains the reliability of tap changers at the lowest temperatures.

Applications

- Mobilect 39 is recommended for use in oil filled transformers and switchgears in which the oil is required as an insulation medium or as a heat transfer medium.
- Mobilect 39 is to be used in applications specifying IEC 60296 -04 General Specifications and reinforced copper corrosion protection (pass ASTM D1275B corrosion test).
- Mobilect 39 is not suitable for use in oil filled cables, for special impregnation processes or for use in capacitors.

Specifications and Approvals

Mobilect 39 meets or exceeds the requirements of:

IEC 60296-04 General Specifications

Typical Properties

Mobilect 39

Density at 20°C, kg/dm ³ , ISO 12185	0.883
Viscosity, mm ² .s-1 @ 40°C, ISO 3104	9.5
Flash Point (PMCC), °C, ISO 2719	148
Pour Point, °C, ISO 3016	- 54
Corrosive Sulphur, ASTM D1275 procedure B	Non Corrosive
Oxidation Stability @ 120°C /164 h, IEC 61 125C	
- Total Acidity, mg KOH/g	0.31
- sludge, wt%	0.11
Dielectric Dissipation Factor @ 90°C, IEC 60247	< 0.001
Interfacial Tension, mN/m, ISO 6295	> 40
Breakdown voltage,	
- before treatment, kV, IEC 60156	> 30

Health and Safety

Based on available information, this product is not expected to produce adverse effects on health when used for the intended application and the recommendations provided in the Material Safety Data Sheet (MSDS) are followed. MSDS's are available upon request through your sales contact office, or via the Internet or will be provided by seller to customers if and as legally required. This product should not be used for purposes other than its intended use. If disposing of used product, take care to protect the environment.

The Mobil logotype, the Pegasus design and Mobilect are trademarks of Exxon Mobil Corporation, or one of its subsidiaries.

5-2012

ExxonMobil Asia Pacific Ltd
1 HarbourFront Place
#06-00 HarbourFront Tower One
Singapore 098633

+65 6885 8000

<http://www.exxonmobil.com>

Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice. All products may not be available locally. For more information, contact your local ExxonMobil contact or visit www.exxonmobil.com

ExxonMobil is comprised of numerous affiliates and subsidiaries, many with names that include Esso, Mobil, or ExxonMobil. Nothing in this document is intended to override or supersede the corporate separateness of local entities. Responsibility for local action and accountability remains with the local ExxonMobil-affiliate entities.

Copyright © 2001-2013 Exxon Mobil Corporation. All rights reserved..

